

Product datasheet

Latest update: 30.01.2012



www.walter-kunststoffe.com
T +43 7246 20355-0, F +43 7246 20355-11
E office@walter-kunststoffe.com

WPT 1371 N

WPT 1371 N is a highly concentrated masterbatch, based on a qualitative high value combination of mineral additive and polymer.

PROPERTIES

Mineral content		70 %
Polymer	PP	30 %
Humidity	ISO 1160	< 500 ppm
Density	ISO 1183	1,7 g/cm ³

MINERAL ADDITIVE

Mineral type	Calciumcarbonate	chalk
Top cut (d ₉₈)		≤ 8,0 μm
Medium particle size (d ₅₀)		≤ 1,8 μm

APPLICATIONS

	Dosage	Costs	CO ₂ -Footprint	Process constance	Output	Printability	Weldability	Soft-Touch	Elongation	Dart-Drop	Elmendorf	Matting
PE blown films ≥ 5 μm	5-30 %	↓	↓	↑	↑	↑	0	↑	0	↑	↑	↑
PE cast films ≥ 7 g/m ²	5-50 %	↓	↓	↑	↑	↑	0	↑	0	-	-	↑
PE blowmoulding	5-15 %	↓	↓	↑	↑	↑	0	↑	0	-	-	↑
PO injection moulding	5-20 %	↓	↓	↑	↑	↑	0	↑	0	-	-	↑
Cleaning aid	50-100 %	↓	↓	↑	↑	-	-	-	-	-	-	-

↓ ... decreasing, ↑ ... increasing, 0 ... remaining unchanged, - ... not relevant

PACKAGINGS

bag, bigbag, octabin, silo-truck

PROCESSING

Predrying is normally not necessary, storage in original packaging and no longer than 6 months recommended. **TIP:** instead of any predrying it is recommended to dose ca. 0,5 % **WPT 2065** on demand.

All informations in that datasheet refer to the here specifically mentioned materials only. For all informations given Walter Kunststoffe GmbH is not guaranteeing for correctness and completeness. There is no admittance of any liability due to usage of materials. It is the user's decision only whether any application is suitable for this material or not.

All delivered goods are remaining property of Walter Kunststoffe GmbH until full payment is done. Bank connection: Oberbank Wels, bank code 15130, account number: 281.3624.26, commercial register number: 303892a, VAT number: ATU 63897901