

WPT 5480 B

WPT 5480 B is a high heat stabilized PP-compound, filled with 80 % Bariumsulfate.

PROPERTIES

color	natural	
Verstärkungsstoff	Bariumsulfat	80 %
Density	ISO 1183	2,4 g/cm ³
Melt Flow Rate (230 °C/2,16 kg)	ISO 1133	0,5 g/10min

APPLICATION

Extrusion and injection moulding, masterbatch

PACKAGING

25 kg bags, Bigbag, Octabin

PROCESSING

Predrying of the material is recommended, as a guideline 2h at 80 °C. Instead of predrying 0,5 % up to max. 2 % of **WPT 2165** is recommended.

STORAGE

WPT 5480B should be stored in dry conditions and at temp. below 50 °C. protect the material from UV-light.